

STOKES BITUMEN PAINTS

Reference MB	Revision No 1	Revision Date 14 October 1999	Printed 15 January 2008	Page 1 of 2
------------------------	-------------------------	---	-----------------------------------	--------------------

WWW.RJSTOKES.CO.UK MANUFACTURERS OF INDUSTRIAL, DECORATIVE & POWDER COATINGS Est 1899
Little London Road | Sheffield | S8 0UH | Tel: 0114 258 9595 | Fax: 0114 250 9836 | Email: sales@rjstokes.co.uk

Properties and Uses	<p>PROPERTIES Attractive appearance with high gloss, good build and opacity. Affords excellent protection inside and outside having outstanding flexibility, adhesion and resistance to weather. Easy to apply and free from brush marks etc., excellent durability and colour retention.</p> <p>USES Stokes Bitumen Paints are recommended for the decoration and protection of exterior surfaces where excellent water and weathering resistance are required. This range of paints can also be used for the protection of machinery and plant etc.</p>
Technical Data	<p>TYPE Bituminous/long oil modified alkyd medium with carefully selected pigments.</p> <p>DRYING TIME About 16 hours to BS3900 part C2 under normal conditions of temperature and humidity. Recoatable overnight.</p> <p>SPREADING CAPACITY About 17 sq. metres per litre on smooth non-porous surfaces.</p> <p>NON VOLATILE CONTENT By volume 42% nominal. Varies slightly with colour. By weight 53% nominal.</p> <p>THINNERS AND CLEANING SOLVENT Stokes White Spirit Ref. TH010.</p> <p>HEAT RESISTANCE Up to 100°C.</p> <p>LEAD CONTENT No added lead. Does not contain lead pigments.</p> <p>COLOUR RANGE Dark Green (Ref. MB004) and Dark Red (Ref. MB005) Other shades to meet customers special requirements can be supplied by arrangement.</p>
Stock Container Sizes	5 litres. Other sizes by arrangement.
Processes	<p>PREPARATION The surface to be painted must be clean, dry and free from grease, dust, dirt, rust and peeling or loose material. New, unpainted or very absorbent surfaces should be primed using the appropriate Stokes material. See Stokes Data Sheets Systems for Metal, Systems for Wood.</p> <p>FINISHING Apply one or preferably two coats if a high standard of durability is required.</p>
Application	<p>BRUSH Supplied ready for use.</p> <p>ROLLER Thinning is not normally required. Mohair or foam rollers are preferable to lambswool to achieve a smoother finish.</p> <p>CONVENTIONAL SPRAY Thin as necessary with Stokes White Spirit Ref. TH010.</p> <p>AIRLESS SPRAY Thin if necessary with Stokes White Spirit Ref. TH010.</p> <p>ELECTROSTATIC SPRAY Adjust conductivity of paint if necessary with Stokes Thinner Ref. TH009.</p>



TECHNICAL DATA SHEET

STOKES BITUMEN PAINTS

Reference	Revision No	Revision Date	Printed	Page 2 of 2
MB	1	14 October 1999	15 January 2008	

WWW.RJSTOKES.CO.UK MANUFACTURERS OF INDUSTRIAL, DECORATIVE & POWDER COATINGS Est 1899
Little London Road | Sheffield | S8 0UH | Tel: 0114 258 9595 | Fax: 0114 250 9836 | Email: sales@rjstokes.co.uk

Storage	<p>Use within 12 months of delivery. Keep in original containers until required for use. Partly used containers should be re-sealed securely and stored according to the recommended manner. (See section 7 of Stokes Material Safety Data Sheet Ref. MB).</p>
Health and Safety	<p>THIS MATERIAL IS FLAMMABLE. REFER TO STOKES MATERIAL SAFETY DATA SHEET REF. MB FOR FULL DETAILS OF FIRST AID, FIRE FIGHTING, ACCIDENTAL RELEASE, HANDLING, EXPOSURE CONTROLS / PERSONAL PROTECTION AND DISPOSAL.</p>
Disclaimer	<p>The above information is for guidance only. It is given in good faith but without warranty. Users should first carry out their own trials to ascertain the suitability of the product for their intended purpose.</p> <p>This Data Sheet supercedes all previous Data Sheets supplied to you relating to this product. It contains important information which must be communicated to the user. The user must satisfy himself of the suitability of the product for the intended application and surface, as surface and application conditions are beyond the control of R.J.Stokes & Co Ltd. The user must also satisfy himself of the suitability of the product in circumstances other than those set out in this data sheet. The user should also maintain appropriate control procedures. Should further information be required, please contact our Technical Department.</p> <p>R.J.Stokes & Co. Ltd. employ a policy of continuous development and the technical data could be revised as a result of experience or new information becoming available.</p>